Product Data

DSM Somos® 9120

a **DSM**Product

Description

DSM Somos® 9120 is a liquid photopolymer that produces robust, functional and accurate parts using stereolithography machines. The material offers superior chemical resistance and a wide processing latitude. With mechanical properties that mimic many engineering plastics, parts created from Somos 9120 exhibit superior fatigue properties, strong memory retention and high quality up-facing and down-facing surfaces. Somos 9120 also offers a good balance of properties between rigidity and functionality.

Application

This photopolymer is used in solid imaging processes, like stereolithography, to build three-dimensional parts. This material is also useful in creating parts for applications where durability and robustness are critical requirements (e.g., automobile components, electronic housings, medical products, large panels and snap-fit parts).

Technical Data: Liquid Properties

Appearance	e Off White	
Viscosity	~450 cps @ 30° C	
Density	1.13 g/cm ³ @ 25° C	

Technical Data: Optical Properties

E _c	10.9 mJ/cm ²	[critical exposure]
D _p	5.60 mils	[slope of cure-depth vs. ln(E) curve]
E ₁₀	65 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]



DSM Somos® 9120 is a liquid photopolymer that produces robust, functional and accurate parts using stereolithography machines.

Key Product Benefits:

- Functional parts
- Durable parts
- Extremely accurate

(continued) Rev Date: 10/09

For technical service, please visit: http://www.dsmsomos.com

Somos[®] **9120**

Technical Data: Mechanical Properties		Somos® 9120 UV Postcure	Polypropylene*
ASTM Method	Property Description	Metric	Metric
D638M	Tensile Strength	30 – 32 MPa	31 – 37.2 MPa
D638M	Elongation at Yield	15 – 25%	7 – 13 %
D638M	Young's Modulus	1,227 – 1,462 MPa	1,138 – 1,551 MPa
D790M	Flexural Strength	44 – 46 MPa	41 – 55 MPa
D790M	Flexural Modulus	1,310 – 1455 MPa	1,172 – 1,724 MPa
D2240	Hardness (Shore D)	80 – 82	N/A
D256A	Izod Impact (notched)	48 – 53 J/m	21 – 75 J/m
D570-98	Deflection Temperature	52 – 61 °C	107 – 121°C

^{*}Unfilled polypropylene (Reference: Modern Plastics Encyclopedia, 1997)

Technical Data: Mechanical Properties		Somos [®] 9120 UV Postcure	Polypropylene*
ASTM Method	Property Description	Imperial	Imperial
D638M	Tensile Strength	4.4 – 4.7 ksi	4.5 – 5.4 ksi
D638M	Elongation at Yield	15 - 21 %	7 – 13%
D638M	Young's Modulus	178 – 212 ksi	165 – 225 ksi
D790M	Flexural Strength	6.0 – 6.7 ksi	6.0 – 8.0 ksi
D790M	Flexural Modulus	190 – 210 ksi	170,000 – 250,000 psi
D2240	Hardness (Shore D)	80 – 82	N/A
D256A	Izod Impact (notched)	0.9 – 1.0 ft-lb/in	0.4 – 1.4 ft-lb/in
D570-98	Deflection Temperature	126 – 142°F	225 – 250 °F

^{*}Unfilled polypropylene (Reference: Modern Plastics Encyclopedia, 1997)

Rev Date: 10/09

DSM

www.dsmsomos.com

DSM Somos® 1122 St. Charles Street Elgin, Illinois 60120 USA

Tel: +1-847-697-0400 Fax: +1-847-468-7785 Applied Rapid Technologies

1130 International Pkwy Fredericksburg,VA 22406 540-286-2266

Fax: 540-286-5252 www.artcorp.com

DSM Desotech-China

476 Li Bing Road Zhangjiang Hi-Tech Park, Pudong New Area Shanghai 201203, China Tel: +(86) 21-6141 8064

NOTICE: DSM Somos is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech sexpressly disclaims any product warranties which may be implied includin warrantie o merchantabilit ad/or fitnes for a particular purpose DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice.