

ST-3050 A/B

50 SHORE A POLYURETHANE ELASTOMER

PRODUCT HIGHLIGHTS:

ST-3050 is a multi-purpose elastomer system that can perform many functions. Product characteristics are:

- ✓ Cures at room temperature to produce a strong, resilient elastomer
- ✓ Easy to use
- ✓ Exudate and volatile free.
- ✓ Maintains a dry, tack free surface after cure

PHYSICAL PROPERTIES:

Hardness, Shore A ASTM D2240	50	5
Density, (g/cc) ASTM D792	1.07	
Cubic Inches per Pound.....	26.2	
Color/Appearance.....	Amber/Translucent	
Tensile Strength, (psi) ASTM D412.....	>1,200*	
Elongation, (%) ASTM D412	>1,400*	
Tear strength, (pli) ASTM D624.....	185	
Shrinkage, (in/in) linear ASTM D2566	0.006	

*Note - Test specimens exceed travel distance of testing equipment.

HANDLING PROPERTIES:

Mix Ratio (by weight):

Part A	100 parts by weight
Part B	50 parts by weight

Mix Ratio (by volume):

Part A	100 parts by volume
Part B	49 parts by volume

Specific Gravity:

Part A	1.05
Part B	1.08

Viscosity (cps) @ 77°F (25°C) Brookfield:

Part A	3,700
Part B	450
Mixed.....	2,600

Color:

Part A	Pale yellow
Part B	Amber*

Work Time, 100g mass @ 77°F (25°C) 20 minutes

Gel Time..... 25 minutes

HANDLING PROPERTIES (continued):

Demold Time @ 77°F (25°C).....3-4 hours

*Note - Part B darkens with time, upon exposure to air.

CURE SCHEDULE/HEAT CURING:

Most of the physical properties can be achieved in 5-7 days at ambient temperature, 77°F (25°C). In order to achieve maximum physical properties, a post cure with heat is required. BJB recommends 24 hours at ambient temperature, 77°F (25°C), followed by 16 hours at 160°F (71°C).

MOLD PREPARATION AND RELEASING:

When ST-3050 A/B is used to reproduce molds from plaster, wood or other porous substrates, we would first recommend that they be sealed. Release agents may then be applied over the sealed surface.

NOTE:

Prolonged direct exposure to sunlight can affect the surface of this product. Cover molds or other products when storing outdoors. **The cure will be inhibited if cast against a tin catalyzed silicone RTV.**

The “A” component may freeze above normal freezing temperatures, 32°F (0°C). If the material appears to have a grainy or lumpy look, heat to 100-120°F (38-49°C) and stir until the material returns to a smooth even consistency. Allow the material to return to ambient temperature, 77°F (25°C), before using.

STORAGE:

Store in a cool dry place. Unopened containers will have a shelf life of 6 months from date of shipments when properly stored at room temperature. Purge opened containers with dry nitrogen before re-sealing.

PACKAGING:

Gallon kits..... 8 lbs. A, 4 lbs. B
5 Gallon kits.....40 lbs. A, 20 lbs. B
55-Gallon drum kits.....400 lbs. A, 200 lbs. B

SAFETY PRECAUTIONS:

Use in a well-ventilated area. Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction. Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product.

IF CONTACT OCCURS:

Skin: Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. It is *not* recommended to remove resin from skin with solvents. Solvents only increase contact and dry skin. Seek qualified medical attention if allergic reactions occur.

Eyes: Immediately flush with water for at least 15 minutes. Call a physician.

Ingestion: If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce vomiting only as directed by medical personnel. Never give anything by mouth to an unconscious person.

Refer to the Material Safety Data Sheet before using this product.

